

GLASS SAND - ST 10

Humidity in a wet state	8,0 % max
Humidity in a dry state	0,2 % max
pH	7,3

Sieves mm	Residue		Bottom
	g	%	%
0,800	0,00	0,03	100,00
0,630	0,06	0,06	99,94
0,500	2,29	2,29	97,65
0,400	17,64	17,64	80,01
0,315	36,83	36,83	43,18
0,200	40,49	40,49	2,69
0,100	2,40	2,40	0,29
< 0,100	0,29	0,29	0,00
Total	100	100	

Fe ₂ O ₃ %	0,010
MK _{calc} Mean grain size mm	0,328
AFS	48,20
d ₅₀ mm:	0,331
d ₇₅ mm:	0,263
d ₂₅ mm:	0,388
log w	53,70
log w %	48,20
S _{th} Theoretical specific surface cm ² /g:	73,26
n _{th} Theoretical specific number of the grains pieces/g	53786,76

